

MOPAK PRINTING PAPERS

Typical Values

Parameter	Unit	Standard	60	70	80	90	100	110	120
Grammage	g/m ²	ISO 536	60	70	80	90	100	110	120
Moisture	%	ISO 287	4,5	4,5	4,5	4,5	4,5	4,5	4,5
Thickness	μ	ISO 534	75	95	105	120	130	140	150
ISO Brightness	Elrepho	ISO 2470	102	102	102	102	102	102	102
CIE W	Elrepho	ISO 11475	145	145	145	145	145	145	145
Opacity	%	ISO 2471	89	92	95	95	95	97	97
Cobb, 60	g/m ²	ISO 535	33	33	33	33	33	33	33

Guaranteed Values

Parameter	Unit	Standard	60	70	80	90	100	110	120
Grammage	g/m ²	ISO 536	±%3	±%3	±%3	±%3	±%3	±%3	±%3
Moisture	%	ISO 287	±% 0,5	±% 0,5	±% 0,5	±% 0,5	±% 0,5	±% 0,5	±% 0,5
Thickness	μ	ISO 534	±%5	±%5	±%5	±%5	±%5	±%5	±%5

The product is available as reels and sheets. It is suitable for UV-offset, colour copying.

Measuring conditions: Relative Humidity - %50 ±2, Temperature 23 ±1oC
Valid starting from January 2019

Production Site: Mopak Kemalpaşa Mill