

MOPAK OFFICE PAPERS

Typical Values

Parameter	Unit	Standard	AVANTAGE	COPY BOSS	MODA COPY	KAZANÇLI OFİS	REKORT
Grammage	g/m ²	TS 3122 EN ISO 536	75	80	80	80	82
Moisture	%	TS EN ISO 287	4,5	4,5	4,5	4,5	4,5
Thickness	μ	TS 3120 EN ISO 20534	101	105	105	105	108
ISO Brightness	Elrepho	TS ISO 2470	100	96	102	103	105
CIE W	Elrepho	TS ISO 11475	150	135	145	155	155
Opacity	%	ISO 2471	95	95	95	95	95
Cobb, 60	g/m ²	ISO 535	33	33	33	33	33

APPLICATIONS



Mopak A4 Office Papers are suitable for usage in all copier, colour laser printers, colour inkjet printers, fax.

Measuring conditions: Relative Humidity - %50 ±2, Temperature 23 ±1oC
Valid starting from January 2019

Production Site: Mopak Kemalpaşa Mill