



Paper Specification
TS – 16.07.2019

SORA medico

SORA medico is a woodfree lightweight uncoated paper.

Parameter	Standard	37	40	45	50	60	Tolerance
Grammage [g/m ²]	ISO 536	37	40	45	50	60	± 2
Thickness [µm]	ISO 534	47	50	56	62	74	± 4
Smoot. Bendtsen [ml/min]	ISO 8791-2	150	150	150	150	150	± 40
Rel. humidity [%]	DIN 53118	47.5	47.5	47.5	47.5	47.5	± 7.5
CIE Whiteness [%]	ISO 11475 (D65/10°)	140	140	140	140	140	± 3
Opacity [%]	ISO 2471	73	76	79	82	86	± 2

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

